

Lisson test	DIN 54322	Score after 6,000 revolutions. Walking zone: 3-4, Stair zone: 3
Vetterman test	DIN 54323	Score: 3 (after 22,000 revolutions)
	NBN G58-019 and SQ/DTR 9405 part 2	Class T5 (ICCO specification)
Tear strength at break	ASTM D 624 C	9.5-12.5 kgf
Tensile strength at break	ISO R 974	13.0 – 15.5 kgf/cm
Bacterial resistance	ASTM G22-70	Resistant (no growth)
UV resistance	GME 00 002 with CI-35 Weatherometer	After 1,000 hours: 3.5 to 5
Use temperature		-25°C to + 45°C